



**INTELLIGENT**  
ROOFING SOLUTIONS

FiberTite® Roofing Systems

## Chemical Reagent Compatibility

Seaman Corporation • 1000 Venture Blvd. • Wooster, OH 44691  
[www.fibertite.com](http://www.fibertite.com)

# Partial Chemical Reagent List Harmful to FiberTite® Membranes

It is important to consider the roof covering whenever you add new products and/or processes to your building operation that will cause chemical contaminant venting onto your roof. The following is a list of chemicals that can cause harm to the FiberTite roof covering, especially if left ponding for several months. Please note that the list of chemicals below is not an exhaustive list. Please send to our attention any specific data pertinent to your needs for us to analyze.

Acetic Acid  
Benzene  
Ethyl Acetate  
Methyl Ethyl Ketone (MEK)  
Phenol  
Solvent Degreasers  
Aromatic Hydrocarbons  
Furfural  
Nitric Acid  
Phosphoric Acid 75%  
Toluene  
Asphalt Materials  
Cooking Oil above 140°F  
Gasoline  
Paint Thinners  
Phthalate Plasticizer Above 100°F  
Xylene

If you have any concerns or questions regarding this list, or any other chemical compatibility issues, please feel free to contact [FiberTite Technical Services](mailto:Technical@FiberTite.com) at: 1-800-927-8578.



FiberTite® is a registered trade name of the Seaman Corporation.  
Copyright © 2015 Seaman Corporation. All rights reserved.



Phone: 330-262-1111 or Toll-free: 800-927-8578  
Fax: 800-649-2737